



Novus Sealing Pty Ltd

15 Vinnicombe Drive,

P.O.Box 1541

Canning Vale WA 6155

Tel (08) 9455 2155

Fax (08) 9455 2165

ACN 057 426 909

ABN 28 057 426 909

Email: mailbox@novussealing.com.au

NOVUS OLEONOID – VEGETABLE FIBRE MATERIAL

ALL PROPERTIES BASED UPON 0.80MM MATERIAL
REFER TO ASTM F104 SECTION 7

PROPERTY	TEST METHOD	UNIT	VALUE
Moisture Content	15 min @ 100°C	%	8 – 14
Thickness	ASTM F104	mm	± 10%
Compression	ASTM F36	%	25- 40
Recovery	ASTM F36	%	40 min
Tensile Strength	ASTM F152	Mn/m ²	13,79
IRM 903 Oil Weight Increase	ASTM F146	%	15 max
IRM 903 Oil Thickness Increase	ASTM F146	%	5 max
Fuel B Weight Increase	ASTM F146	%	15 max
Fuel B Thickness Increase	ASTM F146	%	5 max
Water Weight Increase	ASTM F146	%	90 max
Water Thickness Increase	ASTM F146	%	30 max

DIMENSIONS	
Roll Length	Nominal ± 1% tolerance
Roll Width	For 0,15mm – 0,80mm thickness: 1000 – 1050 mm tolerance For 1,00mm – 6,40mm thickness: 1000 ± 5mm tolerance

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company.